

## BLENDAL STICK MIDNIGHT W/ONYX 973800B70M

## **TECHNICAL DATA SHEET**

PRODUCT NUMBER

DESCRIPTION

M340-0236,M341-0236

BLENDAL STICK MIDNIGHT W/ONYX 973800B70M

PRODUCT DESCRIPTION:

N/A

## PHYSICAL PROPERTIES AND SPECIFICATIONS

| Technology                | N/A  |
|---------------------------|--|
| Color                     | N/A  |
| Sheen                     | N/A  |
| Viscosity                 | N/A  |
| WPG                       | 10.882620520 lbs/gal                               |
| Solids by Volume          | 98.824576631 ±1%                                   |
| Solids by Weight          | 99.049971499 ±1%                                   |
| Flash Point               | 999.00000000 °F                                    |
| HMIS                      | H: 2, F: 0, R: 0, P: X                             |
| Coating VOC (g/I)         | 12.388570077 g/l                                   |
| Coating VOC (Lb/Gal)      | 0.103387997 lbs/gal                                |
| Material VOC (g/l)        | 12.388570129 g/l                                   |
| Material VOC (Lb/Gal)     | 0.103448416 lbs/gal                                |
| #VOC/#Solid               | 0.009591406 lbs/lbs solid                          |
| VHAP Ratio (#VHAP/#Solid) | 0.00000000   |
| Spread Rate               | 1585.146209161 sq. ft./gal @ 1.0 mil DFT (no loss) |
| Catalyst/Ratio            | N/A  |
| Reducer                   | N/A  |
| Retarder                  | N/A  |
| AirDry                    | N/A  |
| Oven Dry                  | N/A  |
| Shelf-Life (Unopened)     | 36 months  |
| Pot-Life (Catalyzed)      | N/A  |
| Recoat Instruction        | N/A  |
| PH                        | N/A  |

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.