



ENDURAGREEN® W/B BRUSHING URETHANE SATIN

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

A29C2140BPQT

ENDURAGREEN® W/B BRUSHING
URETHANE SATIN

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Waterborne Acrylic Urethane
Color	Clear
Sheen	40 +/- 4
Viscosity	30" ± 2 Ford 4 cup @ 77° F
WPG	8.55 lbs/gal
Solids by Volume	26.13 ±1%
Solids by Weight	28.34 ±1%
Flash Point	200.00 °F
HMIS	H: 2, F: 1, R: 0, P: X
Coating VOC (g/l)	273.46 g/l
Coating VOC (Lb/Gal)	2.28 lbs/gal
Material VOC (g/l)	100.74 g/l
Material VOC (Lb/Gal)	0.84 lbs/gal
#VOC/#Solid	0.35 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.04
Spread Rate	419.11 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	Water if needed. Clean up with warm soapy water.
Retarder	N/A
Air Dry	Recoat in one hour in standard conditions 77° F @ 50% humidity. Adjust as needed in damp or cool conditions.
Oven Dry	N/A
Shelf-Life (Unopened)	6 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	Scuff sand with 320 grit steared sandpaper between all coats for proper bonding.
PH	N/A

Maximum dry film thickness for total system not to exceed 4 dry mils

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. SDS and CPDS sheets are available upon request. Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data. The following definitions are being utilized for HAP content: "HAPS-Compliant": < or = .8 lb. HAPS/Lb. Solids; "Low-HAPS": <.5 Lb. HAPS/Lb. Solids; "Ultra-Low-HAPS": <.2 Lb. HAPS/Lb. Solids; "HAPS-Free": <.00 Lb. HAPS/Lb. Solids. HAP content is based upon the presence of HAP compounds utilizing limits as defined in 29 CFR 1910.1200. Manufacturer assumes no liability for use of this information which is intended to serve as a general guide.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Finishworks™, Division of RPM Industrial Coatings Group, Inc. All rights reserved.