



ENDURAGREEN® UNIVERSAL WHITE PRIMER

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

A68CW00030 (5),A68W00045 (1),A68W00045BPR1,A68W 00045BPR1- LA,A68W00045OHAW,A68 W00045OHAW- LA,A68W00045WP5S,A68W 00045WP5S- LA,A68W00045WPTT	ENDURAGREEN® UNIVERSAL WHITE PRIMER
---	--

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Waterborne Acrylic Primer
Color	White
Sheen	Flat Primer
Viscosity	19 +/-2 Seconds #3 Signature Zahn Cup
WPG	13.28 lbs/gal
Solids by Volume	44.98 ±1%
Solids by Weight	65.12 ±1%
Flash Point	200.00 °F
HMIS	H: 2, F: 1, R: 0, P: X
Coating VOC (g/l)	149.49 g/l
Coating VOC (Lb/Gal)	1.25 lbs/gal
Material VOC (g/l)	80.10 g/l
Material VOC (Lb/Gal)	0.67 lbs/gal
#VOC/#Solid	0.08 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.00
Spread Rate	721.47 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	Ready to spray. Use water only if needed for proper atomization.
Retarder	None needed
Air Dry	15-20 Minutes to handle at Room Temperature and 30-70 % humidity.
Oven Dry	Customer Specific
Shelf-Life (Unopened)	6 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	Apply 4-5 wet mils. Dry 45 min to sand with 320. Apply 4-5 mils 2nd coat, dry minimum 1 hr. Sand with 320 prior to topcoat.
PH	N/A

Use only C33 Colorants. 15% max tint loads for most colors. Burnt Umber and Quin Red use at 2% max. Do not use 896 colorants!

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. SDS and CPDS sheets are available upon request. Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data. The following definitions are being utilized for HAP content: "HAPS-Compliant": < or = .8 lb. HAPS/Lb. Solids; "Low-HAPS": <.5 Lb. HAPS/Lb. Solids; "Ultra-Low-HAPS": <.2 Lb. HAPS/Lb. Solids; "HAPS-Free": <0.00 Lb. HAPS/Lb. Solids. HAP content is based upon the presence of HAP compounds utilizing limits as defined in 29 CFR 1910.1200. Manufacturer assumes no liability for use of this information which is intended to serve as a general guide.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Finishworks™, Division of RPM Industrial Coatings Group, Inc. All rights reserved.