

COLORED LACQUER BLACK SATIN

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

L41K6240L1

COLORED LACQUER BLACK SATIN

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Nitrocellulose lacquer
Color	Black
Sheen	48° ± 2
Viscosity	24"±1, Zahn #3 Sig
WPG	7.72 lbs/gal
Solids by Volume	20.38 ±1%
Solids by Weight	26.96 ±1%
Flash Point	-4.00 °F
HMIS	H: 2, F: 3, R: 0, P: X
Coating VOC (g/l)	668.43 g/l
Coating VOC (Lb/Gal)	5.58 lbs/gal
Material VOC (g/l)	631.39 g/l
Material VOC (Lb/Gal)	5.27 lbs/gal
#VOC/#Solid	2.53 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.59
Spread Rate	326.83 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	1:1 reduction with T84C0020 Lacquer Reducer
Retarder	T84C0023 No Blush Retarder 10% maximum addition by volume
Air Dry	1 hour dry between coats @ 77° F, 35% relative humidity
Oven Dry	User specific
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	N/A
PH	N/A

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. SDS and CPDS sheets are available upon request. Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data. The following definitions are being utilized for HAP content: "HAPS-Compliant": < or = .8 lb. HAPS/Lb. Solids; "Low-HAPS": <.5 Lb. HAPS/Lb. Solids; "Ultra-Low-HAPS": <.2 Lb. HAPS/Lb. Solids; "HAPS-Free": <0.00 Lb. HAPS/Lb. Solids. HAP content is based upon the presence of HAP compounds utilizing limits as defined in 29 CFR 1910.1200. Manufacturer assumes no liability for use of this information which is intended to serve as a general guide.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.